

DESCRIPTION			
Total Thickness	EN 428	mm	1.00 +/- 0.15
Stabilization			CaZn
Density		g/cm ³	1.49
Weight	EN 430	g/m ²	1400 +/-200
Panels width	EN 426	mm	600
Panels lengths	EN 426	mm	400 (classic) 600 (fountain)
Surface			textured
CLASSIFICATION			
Fire reaction	EN 13 501-1	class	B-s2,d0
	NFP 92 – 507	class	M1
	BSI	class	0
	ASTM 84	class	A

PERFORMANCE			
Chemicals resistance			Anios compliant
			H2O2 compliant
Decontamination of surface (radionuclide)	ISO 8690		excellent
anti-bacterial activity (E. coli – S. aureus – MRSA) (1)	JIS Z 2801	-	> 99% inhibits growth
TVOC emission	EN 16000-6	after 28 days	< 15µg/m3
Welding resistance with Gerflor contract vinyl flooring (wearlayer > 0,5mm)	NF-EN 684	DaN/5cm	>24

(1) The implementation of an effective cleaning method is the best defence against infection.